

Christy[®] Pak Ceramic Raschig Rings

FEATURES

- High mechanical strength
- Economical
- High available surface area
- Well-proven in thousands of installations worldwide
- Water Absorption: < 1%



PACKING DATA

Nominal Diameter	Density	Surface Area	Free Space	Wall Thickness*
in (mm)	lb/ft ³ (kg/m ³)	Ft ² /ft ³ (m ² /m ³)	(%)	in (mm)
¼ (6)	60 (961)	217 (712)	62	0.06 (1.6)
½ (12.5)	50 (800)	112 (367)	64	0.10 (2.6)
5/8 (16)	46 (730)	93 (305)	73	0.13 (3.3)
¾ (19)	44 (705)	74 (243)	72	0.14 (3.5)
1 (25)	40 (640)	58 (190)	74	0.14 (3.5)
1.5 (38)	35 (560)	37 (121)	73	0.19 (4.8)
2 (50)	33 (528)	29 (93)	77	0.24 (6.0)
3 (76)	31 (497)	19 (65)	78	0.33 (8.5)
4 (100)	31 (497)	18 (60)	80	0.33 (8.5)

*Note: The wall thickness shown in the table above is the standard thickness for each size. Different wall thickness is also available.

Christy Catalytics, LLC offers a complete range of catalyst bed supports, tower packings and tower internals.